#### HIGH RELIABILITY "SR" CAPACITORS

#### (TESTED SIMILARLY TO MIL-PRF-123-GROUP A)

For applications that require a high level of reliability, Presidio recommends its high reliability "SR". Tested similarly to MIL-PRF-123 Group A only. Presidio manufactures this SR series on the same manufacturing line as its military products. They may be used both in military and some space applications. Please note that these capacitors are NOT MIL-qualified, nor are they the highest level of reliability for space applications. Several space level series are available. Our most popular series for space comes from the NASA drawing S311P829. Please contact factory for more info.

#### **QUALITY ASSURANCE PROVISIONS**

Every lot undergoes the following inspection and tests:

- a) Destructive Physical Analysis (DPA) A representative sample is pulled from each lot and examined per relevant sections of EIA 469 and to verify adherence to Presidio's internal design criteria. Sample size is per MIL-PRF-123.
- b) Ultrasonic Scanning (optional) This screening may be performed on lots to assure the highest quality microstructure. Ultrasonic scanning is not required for each lot, and must be specified on the customer purchase order.
- c) Thermal Shock All parts are temperature cycled for 20 cycles in accordance with MIL-PRF-123.
- d) Voltage Conditioning All parts receive a voltage conditioning at 2X rated voltage and 125°C for a minimum of 168 hours and a maximum of 264 hours. Voltage conditioning may be terminated at any time between 168 and 264 hour time intervals when failures are less than .1% or 1 piece, during the last 48 hours of the test. Tested in accordance with MIL-PRF-123 except resistors are used in place of fuses.
- e) Insulation Resistance (IR @ 125°C) All parts are tested at 125°C and rated voltage in accordance with Method 302 of MIL-STD-202. The minimum IR required is 10,000 megohms or 100 megohm-microfarads.
- f) Dielectric Withstanding Voltage (DWV) All parts are tested at 2.5X rated voltage in accordance with Method 301 of MIL-STD-202, or according to EIA/MIL Standards.
- g) Insulation Resistance (IR @ 25°C) All parts are tested at 25°C and rated voltage in accordance with Method 302 of MIL-STD-202. The minimum IR required is 100,000 megohms or 1,000 megohm-microfarads.
- h) Capacitance All parts are tested at 25°C and 1VACRMS in accordance with Method 305 of MIL-STD-202.
- i) Dissipation Factor (DF) See following table:

Voltage Rating	NPO	BX/BR	X7R 7.5% 7.5% 5.0% 3.5%	
10	N/A	5.0%		
16	.15%	5.0%		
25	.15%	3.5%		
50	.15%	2.5%		
> 50	.15%	2.5%	2.5%	

- j) Percent Defective Allowed (PDA) The cumulative PDA after voltage conditioning is 5%. Pieces rejected as out of tolerance for capacitance or visual screening will be removed from the lot but not counted in the PDA calculation.
- k) Visual Performed on pieces in accordance with MIL-PRF-123 Appendix B.
- Mechanical Level 1 AQL 1% in accordance with MIL-PRF-123.
- m)Operating Temperature Range: -55°C to +125°C
- n) (Optional) Class K Element Evaluation per MIL-PRF-38534 Rev L — Must be specified on the RFQ and Purchase Order (charge will apply). Data package included.

#### STANDARD PACKAGING

Product will be packaged in individual waffle trays or tape and reel as specified by customer.

#### **DATA PACKAGE**

Data will be sent with each shipment including:

- a) Certificate of Compliance Certificate of Compliance and attributes test data sheet will be sent with each shipment.
- b) (Optional) Destructive Physical Analysis Report Destructive Physical Analysis (DPA) report and photographs for each lot will be sent. Extra charge may apply.
- c) (Optional) Class K Element Evaluation per MIL-PRF-38534 Rev L — Must be specified on the RFQ and Purchase Order (charge will apply). Data package included.
- d) (Optional) Ultrasonic Examination An ultrasonic scanning report will be included. Must be specified on the RFQ and Purchase Order (charge will apply).

# EXAMPLE PART NUMBER SR0402X7R104LENT91

Add "SR" to the beginning of the standard Presidio part number. See Page 3 "HOW TO ORDER A STANDARD PART"

Visit Presidio's website for additional technical information on these products.



### **HIGH RELIABILITY "SR" CAPACITORS**

SIZE		w	THICKNESS	METALIZATION		DIELECTRIC		
SIZE	L inches (mm)	inches (mm)	MAX. (T) inches (mm)	BAND (M.B.) inches (mm)	WVDC	NPO	ВХ	X7R
0201	0.024 (0.61) 0.003 (0.08)	0.011 (0.28) 0.001 <sup>±</sup> (0.03)	0.013 (0.33)	0.004 (0.10) min. band .008(0.20) min. space	10 V	Contact Factory	Contact Factory	0.01 μF
					10 V	390 pF		0.10 μF
	0.040 (1.02) ± 0.004 (0.10)	0. 020 (0.51)	0.024	0.004 (0.10) min. band	16 V	200 pF	1200 pF	0.010 μF
0402		±	(0.61)	0.015 (0.38) min. space	25 V	120 pF	820 pF	4700 pF
		0. 004 (0.10)		, , , , , , , , , , , , , , , , , , , ,	50 V 100 V	100 pF 39 pF	560 pF	3900 pF
					100 V	1200 pF	330 pF	1200 pF 0.047 μF
	0.040 (1.02)	0. 030 (0.76)	0.03	0.004 (0.10) min. band	16 V	560 pF	3300 pF	0.022 μF
0403	±	±			25 V	390 pF	2200 pF	0.015 μF
	0.010 (0.25)	0. 010 (0.25)	(0.76)	0.015 (0.38) min. space	50 V	330 pF	1500 pF	0.012 μF
					100 V	68 pF	680 pF	2200 pF
			0.04 (1.02)		10 V	2700 pF		0.12 μF
	0.050 (1.27)	0. 040 (1.02)		0.005 (0.13) min. band	16 V	1800 pF	6800 pF	0.082 μF
0504	±	0. 010 (0.25)		0.015 (0.38) min. space	25 V	1500 pF	5600 pF	0.047 μF
	0.010 (0.25)				50 V	1200 pF	3900 pF	0.039 μF
					100 V	180 pF	1800 pF	6800 pF
	0.000 (4.00)	0. 032 (0.81) ± 0. 006 (0.15)	0.035 (0.89)	0.005 (0.13) min. band 0.025 (0.64) min. space	10 V 16 V	2200 pF 1000 pF	4700 pF	0.22 μF 0.10 μF
0603	0.063 (1.60) ±				25 V	680 pF	3300 pF	0.10 μF 0.027 μF
0000	0.006 (0.15)				50 V	560 pF	2200 pF	0.022 μF
	` ,	,			100 V	100 pF	1000 pF	3300 pF
					10 V	4700 pF		1.0 µF
	0.080 (2.03)	0. 050 (1.27)	0.055	0.020 (0.51)	16 V	3300 pF	0.022 μF	0.22 µF
0805	±	±	0.055 (1.40)	± 0.010 (0.25)	25 V	2700 pF	0.018 μF	0.10 μF
	0.010 (0.25)	0. 010 (0.25)	(1.40)		50 V	2200 pF	0.010 μF	0.10 μF
					100 V	560 pF	5600 PF	0.022 μF
				0.020 (0.51) ± 0.010 (0.25)	10 V	0.012 μF	2.222 5	1.8 µF
	0.126 (3.20)	0. 063 (1.60) ± 0. 008 (0.20)	0.050		16 V 25 V	8200 pF	0.082 µF	0.39 µF
1206	± 0.008 (0.20)		0.059 (1.50)		50 V	6800 pF 5600 pF	0.056 μF 0.039 μF	0.27 μF 0.22 μF
			(1.50)		100 V	1500 pF	0.022 μF	0.22 μr 0.068 μF
					200 V	820 pF	0.022 pi	0.027 μF
	0.125 (3.18) ± 0.010 (0.25)	± ±	0.065 (1.65)	0.020 (0.51) ± 0.010 (0.25)	10 V	0.018 μF		2.7 µF
					16 V	0.012 μF	0.22 μF	0.68 µF
1209					25 V	0.010 μF	0.18 μF	0.47 μF
1209					50 V	8200 pF	0.12 μF	0.39 μF
					100 V	3900 pF	0.047 μF	0.15 μF
					200 V	1800 pF	2.00 5	0.068 μF
	0.175 (4.45)	0.405 (0.40)			16 V 25 V	0.027 μF 0.022 μF	0.33 μF 0.22 μF	
1712		0.065	0.020 (0.51) ±	50 V	0.022 μF 0.015 μF	0.22 μF 0.18 μF	1.0 μF 0.68 μF	
1712			5) (1.65)	0.010 (0.25)	100 V	6800 pF	0.068 μF	0.00 μl 0.27 μF
		, ,			200 V	3300 pF	0.000 р.	0.12 μF
1812	0.180 (4.572) ± 0.015 (0.38)	0.125 (3.18) ± 0.015 (0.38)	0.080 (2.03)	0.020 (0.51) ± 0.010 (0.25)	10 V	N/A	N/A	4.7 μF
	0.175 (4.45) ± 0.015 (0.38)	± ±	0.065 (1.65)	0.020 (0.51) ± 0.010 (0.25)	16 V	0.068 μF	0.82 μF	3.3 µF
					25 V	0.056 μF	0.56 μF	2.2 µF
1725					50 V	0.039 μF	0.47 µF	1.8 µF
					100 V	0.018 µF	0.22 μF	0.68 μF
	0.220 (5.59) ± 0.015 (0.38)	± ±	0.08 (2.03)	0.020 (0.51) ± 0.010 (0.25)	200 V 16 V	8200 pF 0.082 μF	1.2 µF	0.27 μF 3.9 μF
					25 V	0.082 μF 0.068 μF	1.2 μF 1.0 μF	3.9 µF
2225					50 V	0.056 μF	0.68 μF	2.2 μF
_ LLLO					100 V	0.027 μF	0.33 μF	1.0 μF
		,			200 V	0.012 μF	2.00 p.1	0.47 μF

Note: Above parts are tested similarly to MIL-PRF-123 Group A only. (Ultrasonic exam not included; can be ordered as an option.) Presidio has the ability to add Group B for space applications. Call the factory for more information.

## HOW TO ORDER HIGH RELIABILITY "SR" CAPACITORS (See p. 3, Example: SR0402X7R104LENT91)

I	SR	0402	X7R	104	L	E	NT9	1	_
	Prefix	Case Size	Dielectric Code	Capacitance Code 0.1 µF	Tolerance Code -10% / +20%	Voltage Code 10 V	Termination Code Ni/SnPb	Marking & Packaging Reel, unmarked	Blank = Non-RoHS R = RoHS Compliant